



Product features

- Methanol based single component room temperature curing silicone adhesive sealant
- Excellent insulation, moisture resistance, earthquake resistance, corona resistance, leakage resistance, and chemical resistance properties
- Has good sealing and adhesion to most metal and non-metal materials
- Fully comply with EU directives such as ROHS and REACH

Typical application

- Waterproof, moisture-proof, and adhesive properties of sensors, guardrail tube lamps, mirrors, electrical equipment, optical instruments, and other products
- Coating protection for pins of electronic components such as PCB sensitive elements, capacitors, and transistors.

instructions

1. Clean the surface: clean the surface of the adhered or coated object to remove rust, dust and oil stains.
2. Sizing: cut the front tip, put on a pointed mouth, and use a special glue dispenser or manual glue applicator to size the electronic adhesive on the position of electronic and electrical components to be bonded, generally evenly smeared. According to the product specification, it is allowed to stand and cure to ensure the bonding effect.
3. After the operation is completed, the unused glue should be immediately tightened and sealed.

technical parameter

| project | reference standard | HCJ-308ZJ |
|---------------------------------------|---------------------------------------|-----------------------|
| colour | estimate range by eye | white |
| condition | estimate range by eye | No-flow |
| Relative density (g/cm ³) | GB/T533-2008 | 1.5±0.1 |
| Surface drying time (min) | GB/T13477.5-2002 | ≤15 |
| Hardness (shore A) | GB/T531.1-2008 | 50±5 |
| Elongation at break (%) | GB/T528-2009 | ≥160 |
| Shear strength (MPa) | GB/T7124-2008 | ≥1.0 |
| Tensile strength (Mpa) | GB/T528-2009 | ≥1.8 |
| Volume resistivity (ω cm) | GB/T1692-2008 | ≥2.3×10 ¹⁵ |
| Insulation breakdown strength (Kv/mm) | GB/T1695-2005 | ≥20 |
| Dielectric constant (100MHz) | GB/T1697-2003 | 3.2 |
| Temperature range (°C) | Actual measurement of use environment | -50~150 |
| Viscosity (cps) | GB/T 2794-1995 | 150000-200000 |

Note: The above performance data are all measured at 25°C and 55% relative humidity after molding for one day. Our company is not responsible for the data difference caused by different test strips or product improvement, and the image may be different from the original product.

matters need attention

1. After the operation is completed, the remaining glue should be sealed and preserved to avoid colloid solidification. When using it again, remove a little crust from the seal before using it.
2. Accidentally contact the skin, wipe it clean, and then rinse it with water; In case of accidental contact with eyes, immediately rinse with clear water and go to the hospital for examination. Please refer to the MSDS of the product for safety data.

Storage requirements

1. This product is non-toxic and non-dangerous, so it can be handled and transported according to general chemicals. Pay attention to seal tightly after use and store in a cool, dry and ventilated place.
2. This product should be stored in RH environment with temperature of 5°C-38°C and humidity of 35%-75% for 6 months.

packing specifications

100ML/ 100 PCs/box;
300ML/ piece,
25pieces/box;
2.6L/piece,4 pieces/box;
Can be customized according to customer requirements.

special explanation

The data in this manual are obtained under laboratory conditions. Due to the differences in the use environment, users should refer to these data and use conditions for analysis and test. Kuayue Electronics does not guarantee the sale of products and the use of Kuayue Electronics products under specific working conditions, and does not assume any direct, indirect or accidental losses. If users encounter any problems in the use process, they can contact the service department of Leapfrog Electronic Technology, and we will provide you with all the help.